


Features and Benefit

- Thermally conductive phase change material
- Excellent anti-piercing properties
- Excellent dielectric properties
- Naturally tacky
- RoHS compliant
- Halogen-free



OC-9100 is a thermally conductive phase change material coated on polyimide film. The liquid phase of the material can fill interface irregularities with much higher efficiency than traditional gap filler while the polyimide layer offers excellent anti-pierce and dielectric properties.

OC-9100 is RoHS compliant and conforms to halogen-free standard. It is naturally tacky and additional adhesive is generally not required.

Typical Application

- Discrete power semiconductors
- Power supply modules
- Audio and video component
- General high pressure interface
- Micro processor

Color

- White (PCM)
- Amber (PI film)

Standard Configurations

- Thickness: 0.01" - 0.02" (0.25mm-0.50mm)
- Sheet size: 12" x 16"
- Please consult our factory for alternative thicknesses and die-cut options

Optional Configuration

- Adhesive coatings are optional
- Aluminium foil/laminate is optional

Typical Properties

OC-9100	Typical Data	Test Method
Construction & Composition	Phase change materials coated on both sides of polyimide film	—
Color	White	Visual
Thickness Range (inch)/(mm)	0.01" ~ 0.02"(±0.002) 0.25 ~ 0.50mm (±0.05)	—
Polyimide Film Thickness(mm)	0.05	—
Shelf life(months)	12	—
Phase change temperature range (°C)	50 °C ~ 65 °C	—
Temperature Range (°C)	-40 °C ~ 130 °C	—
Thermal Impedance @ 80psi (°C.in ² /W)	0.37	ASTM D5470 (Modified)
Burn-in temperature (°C)	75 °C for 5 minutes	—
Breakdown Voltage (V)	>8000(Thickness≥0.01")	ASTM D149
Thermal Conductivity (W.m ⁻¹ .K ⁻¹)	1.0	ASTM D5470 (Modified)

SEM (North America) Inc.

Tel: +1 585-643-2000
 Fax: +1 585-427-7216
 Address: 1600 Lexington Ave., Suite 236A
 Rochester, NY 14606, USA

SEM Belgium bvba

+32 59 560 270
 +32 59 560 271
 Slijpesteenweg 28,
 8432 Middelkerke (Leffinge), Belgium


SEM (Far East) Ltd.

+852 2686 9872
 +852 2686 9728
 Unit 3, 3/F, Blk A, New Trade Plaza,
 No. 6 On Ping St., Shatin, N.T., Hong Kong.

SEM (Dongguan) Ltd.

+86-769-8356 5686
 +86-769-8334 2028
 No.8 Qiaoxin Rd., Qiaotou Dongguan,
 Guangdong, China, 523525.

Specifications and appearances may change without notice. All statements, technical information and recommendations herein are based on tests that we believed to be reliable, but the accuracy and completeness are not guaranteed. Before using, user should determine the suitability of the product for its intended use, and the user assumes all risks and liabilities whatsoever in connection therewith. Neither the seller nor the manufacturer shall be liable for any loss or damage, direct, incidental or consequential, including loss of profits or revenues arising from the use or inability to use the product. Any statements or recommendations shall have no effect unless contained in an agreement signed by authorized personnel of the seller and manufacturer.



SEM (North America) Inc.

Tel: +1 585-643-2000
 Fax: +1 585-427-7216
 Address: 1600 Lexington Ave., Suite 236A
 Rochester, NY 14606, USA

SEM Belgium bvba

+32 59 560 270
 +32 59 560 271
 Slijpesteenweg 28,
 8432 Middelkerke (Leffinge), Belgium

SEM (Far East) Ltd.

+852 2686 9872
 +852 2686 9728
 Unit 3, 3/F, Blk A, New Trade Plaza,
 No. 6 On Ping St., Shatin, N.T., Hong Kong.

SEM (Dongguan) Ltd.

+86-769-8356 5686
 +86-769-8334 2028
 No.8 Qiaoxin Rd., Qiaotou Dongguan,
 Guangdong, China, 523525.

Specifications and appearances may change without notice. All statements, technical information and recommendations herein are based on tests that we believed to be reliable, but the accuracy and completeness are not guaranteed. Before using, user should determine the suitability of the product for its intended use, and the user assumes all risks and liabilities whatsoever in connection therewith. Neither the seller nor the manufacturer shall be liable for any loss or damage, direct, incidental or consequential, including loss of profits or revenues arising from the use or inability to use the product. Any statements or recommendations shall have no effect unless contained in an agreement signed by authorized personnel of the seller and manufacturer.