

Features and Benefits

- Superior thermal performance
- 2.3 W/m-K thermal conductivity
- Good EMI suppression
- RoHS compliant
- Halogen-free



Typical Applications

- Notebook Computers
- Handheld Portable Electronics
- Micro Heat Pipe assemblies
- Micro Processors, Memory Chips and Graphic Processors
- Motor Control
- Wireless Communication Hardware

Optional Configurations

- Can be die-cut into specific dimensions

OP-7400 offers hybrid absorber/thermal management material that is used for EMI mitigation. Designed using silicone gel binder that imparts inherent tack typical of standard thermal gap fillers. Filler particle composition imparts both excellent thermal conductivity and good EMI suppression in the microwave frequency.

The proprietary formulation of OP-7400 is RoHS compliant and halogen-free, providing extra reassurance in applications where hazardous substances are forbidden.


Properties	OP-7400	Test Method
Construction & Composition	Soft silicone elastomer	—
Color	Dark grey	Visual
Thickness Range /inch (mm)	0.02"~0.12" (0.508~3.048) in 0.01" (0.254) increments	—
Standard Sheet Size	9" x 9"	—
Density /g.cm ⁻³	4.4	ASTM D792
Hardness /Shore 00	60	ASTM D2240
Tensile Strength /psi	32	ASTM D638
UL Flammability Rating	UL94 V0	UL
Temperature Range /°C	-40°C~175°C	—
Thermal Conductivity W.m ⁻¹ .K ⁻¹	2.3	ASTM D5470 (modified)
Volume Resistivity /ohm.cm	2.0 x 10 ¹²	ASTM D257
EMI Attenuation @ 10 GHz	70 dB/cm	—
Shelf Life /Months	12	—

Please contact us for other requirements

Carrier Treatment	Criteria
Fiber Glass (FG)	Not Recommended
Rubberized Cloth (RC)	Not Recommended
Pressure Sensitive Adhesive (PSA)	Not Recommended
Detachable Adhesive (DA)	Not Recommended
Aluminum Foil (AL)	Not Recommended
Kapton (PI)	Not Recommended
Talc treatment (DAT)	Not Recommended

Product Code and Descriptions

OP 74 XX - XX - XX - XX - XX



SEM (North America) Inc.

Tel: +1 585-643-2000
Fax: +1 585-427-7216
Address: 1600 Lexington Ave., Suite 236A,
Rochester, NY 14606,
USA

SEM Belgium bv

+32 59 560 270
+32 59 560 271
Slijpesteenweg 28,
8432 Middelkerke (Leffinge),
Belgium


SEM Asia Ltd.

+852 2686 9872
+852 2686 9728
Unit 3, 3/F, Blk A, New Trade Plaza,
No. 6 On Ping St., Shatin, N.T.,
Hong Kong.


SEM (Dongguan) Ltd.

+86-769-8356 5686
+86-769-8334 2028
No.8 Qiaoxin Rd., Qiaotou Dongguan,
Guangdong, China, 523525.

Thermal Impedance of OP-7400



Attenuation of OP-7400



SEM (North America) Inc.

Tel: +1 585-643-2000
 Fax: +1 585-427-7216
 Address: 1600 Lexington Ave., Suite 236A,
 Rochester, NY 14606,
 USA

SEM Belgium bv

+32 59 560 270
 +32 59 560 271
 Slijpesteenweg 28,
 8432 Middelkerke (Leffinge), Belgium

SEM Asia Ltd.

+852 2686 9872
 +852 2686 9728
 Unit 3, 3/F, Blk A, New Trade Plaza,
 No. 6 On Ping St., Shatin, N.T., Hong Kong.

SEM (Dongguan) Ltd.

+86-769-8356 5686
 +86-769-8334 2028
 No.8 Qiaoxin Rd., Qiaotou Dongguan,
 Guangdong, China, 523525.