


Features and Benefits

- 10.0W/m-K thermal conductivity
- Naturally tacky
- RoHS compliant
- Halogen-free



Typical Applications

- Notebook Computers
- Power conversion equipments
- Power supplies
- Large telecommunication switching hardware

Optional Configurations

- Can be die-cut into other dimensions

The proprietary metal filler formula of OP-9700 offers superior thermal performance with moderate compressibility.

This thermally conductive gap filler is RoHS and halogen-free compliant. It is suitable for applications where high thermal performance and stringent control of hazardous constituents are required.

OP-9700 is naturally tacky. Additional adhesive is generally not required.


Properties	OP-9700 Series	Test Method
Construction & Composition	Soft silicone elastomer	—
Color	Grey	Visual
Thickness Range /inch (mm)	0.02"~0.4" (0.508 ~10.16) in 0.01" (0.254) increments	—
Standard Sheet Size	9" x 9"	—
Density /g.cm ⁻³	2.50	—
Hardness /Shore 00	60	ASTM D2240
UL Flammability Rating	UL94 V0	—
Temperature Range /°C	-40°C~200°C	—
Thermal Conductivity /W.m ⁻¹ .K ⁻¹	10.0	ASTM D5470 (modified)
Shelf Life /Months	24	—

Please contact us for other special requirements

Carrier Treatment	Criteria
Fiber Glass (FG)	Not Recommended
Rubberized Cloth (RC)	Not Recommended
Pressure Sensitive Adhesive (PSA)	Not Recommended
Detachable Adhesive (DA)	Not Recommended
Aluminum Foil (AL)	Not Recommended
Kapton (PI)	Not Recommended
Talc treatment (DAT)	Not Recommended

Product Code and Descriptions

OP 97 XX - XX - XX - XX - XX



Dimensions
SS = Standard sheet size
CD = Custom dimensions

Release Liner
ST = Standard
OT = Other

PSA
00 = No PSA
A1 = One side
A2 = Both sides

Carrier
00 = No Carrier

Thickness (mil)
00 = Custom thickness
04 = 40mil

97 = 9700 Series
OP = OpTIM™ gap filler

SEM (North America) Inc.

Tel: +1 585-643-2000
Fax: +1 585-427-7216
Address: 1555 Jefferson Road,
Rochester, NY 14623

SEM Belgium bv



+32 59 560 270
Schattig 73,
8210 Zedelgem, Belgium

SEM Asia Ltd.

+852 2686 8168
+852 2686 8268
Unit 1, 3/F Block A, New Trade Plaza,
6 On Ping Street, Shatin, N.T., Hong Kong

SEM (Dongguan) Ltd.

+86-769-8334 1628
+86-769-8334 2028
No. 8A Qiaoxin Road, Qiaotou,
Dongguan, Guangdong, China
Postal code 523525



SEM (North America) Inc.

Tel: +1 585-643-2000
 Fax: +1 585-427-7216
 Address: 1555 Jefferson Road,
 Rochester, NY 14623

SEM Belgium bv

+32 59 560 270
 Schatting 73,
 8210 Zedelgem, Belgium

SEM Asia Ltd.

+852 2686 8168
 +852 2686 8268
 Unit 1, 3/F Block A, New Trade Plaza,
 6 On Ping Street, Shatin, N.T., Hong Kong

SEM (Dongguan) Ltd.

+86-769-8334 1628
 +86-769-8334 2028
 No. 8A Qiaoxin Road, Qiaotou,
 Dongguan, Guangdong, China
 Postal code 523525