


The OP-400 series is made from high-quality Natural Flake Graphite, through special processes and expanded under high temperature.

Properties:


High and low temperature resistance

High corrosion resistance



Applications:

It can be used to manufacture Graphite Braided Packing, Spiral Wound Gasket, Metal Reinforced Graphite Plate...etc.



Properties	OP-400 Series	Test Method
Construction & Composition	Flexible Graphite	—
Carbon Content /%	≥99.5	—
Color	Pewter	Visual
Thickness Range /inch (mm)	0.002~0.06" (0.051~1.524mm)	—
Density /g.cm ⁻³	1.2	—
Hardness /Shore A	85	ASTM D2240
Tensile Strength /Mpa	≥4.6	ASTM D412
UL Flammability Rating	UL94 V0	—
Temperature Range /°C	-40~300°C	—
Thermal Conductivity -Z Axis /W.m ⁻¹ .K ⁻¹	>5	ASTM D5470 (modified)
Thermal Conductivity -XY Axis /W.m ⁻¹ .K ⁻¹	>400	ASTM D5470 (modified)
Volume Resistivity (In-Plane) /ohm.cm	11 x 10 ⁻³	ASTM D991
Thermal Impedance @ 80 psi (10mil)	0.162 °C-in ² /W	ASTM D5470 (modified)
Shelf Life /Months	24	—

Please contact us for other special requirements

SEM (North America) Inc.

Tel: +1 585-643-2000
 Fax: +1 585-427-7216
 Address: 1555 Jefferson Road,
 Rochester, NY 14623

SEM Belgium bv

+32 59 560 270
 Schatting 73,
 8210 Zedelgem, Belgium

SEM Asia Ltd.

+852 2686 8168
 +852 2686 8268
 Unit 1, 3/F Block A, New Trade Plaza,
 6 On Ping Street, Shatin, N.T., Hong Kong

SEM (Dongguan) Ltd.

+86-769-8334 1628
 +86-769-8334 2028
 No. 8A Qiaoxin Road, Qiaotou,
 Dongguan, Guangdong, China
 Postal code 523525

Specifications and appearances may change without notice. All statements, technical information and recommendations herein are based on tests that we believed to be reliable, but the accuracy and completeness are not guaranteed. Before using, user should determine the suitability of the product for its intended use, and the user assumes all risks and liabilities whatsoever in connection therewith. Neither the seller nor the manufacturer shall be liable for any loss or damage, direct, incidental or consequential, including loss of profits or revenues arising from the use or inability to use the product. Any statements or recommendations shall have no effect unless contained in an agreement signed by authorized personnel of the seller and manufacturer.