

# OP-8100 Spec 06

#### THERMALLY CONDUCTIVE GAP FILLER

## **Features and Benefits**

- 2.5W/m-K thermal conductivity
- Moderate compressibility
- Cost effective
- Electrically isolating



#### **Typical Applications**

- Notebook and desktop computers
- Memory modules
- Heat pipe assemblies
- HDDs and DVDs
- Flat-panel displays
- Telecommunication hardware

### **Optional Configurations**

Can be die-cut into specific dimensions


OP-8100 Spec 06 is a performance-improved derivative of the original OP-8100 gap filler. This special feature is benefited from a revised metal oxide filler matrix. It is electrically non-conductive and conforms to UL94 V0 standard. OP-8100 Spec06 is ROHS compliant and halogen free.

Properties	OP-8100 Spec 06	Test Method
Construction & Composition	Soft silicone elastomer	=
Color	Grey	Visual
Thickness Range /inch (mm)	0.01"~0.03" (0.25~0.75)	_
Standard Sheet Size	12" x 16"	+ (1)
Density /g.cm-3	2.65	
Hardness /Shore 00	60	ASTM D2240
UL Flammability Rating	UL94 V0	
Temperature Range /°C	-40~200°C	
Thermal Conductivity W.m-1.K-1	2.5	ASTM D5470 (modified)
Breakdown Voltage / V	>4000V (Thickness $\geqslant$ 0.3mm) >4500V (Thickness $\geqslant$ 0.4mm) >5000V (Thickness $\geqslant$ 0.5mm)	ASTM D149
Shelf Life /Months	24	

Please contact us for other requirements

Carrier Treatment	Criteria	
Fiber Glass (FG)	Compulsory for ≤ 0.012" (0.3mm)	
Rubberized Cloth (RC)	Not Recommended	
Pressure Sensitive Adhesive (PSA)	Not Recommended	
Detachable Adhesive (DA)	Not Recommended	
Aluminum Foil (AL)	Not Recommended	
Kapton (PI)	Not Recommended	
Talc treatment (DAT)	Not Recommended	

#### **Product Code and Descriptions**



SEM (North America) Inc.

+1 585-643-2000 +1 585-427-7216 1555 Jefferson Road, Rochester, NY 14623

Tel: Fax:

Address

**SEM Belgium bv** +32 59 560 270

Schatting 73, 8210 Zedelgem, Belgium SEM Asia Ltd.

+852 2686 8168 +852 2686 8268 Unit 1, 3/F Block A, New Trade Plaza, 6 On Ping Street, Shatin, N.T., Hong Kong SEM (Dongguan) Ltd.


+86-769-8334 1628 +86-769-8334 2028 No. 8A Qiaoxin Road, Qiaotou, Dongguan, Guangdong, China

Postal code 523525
Specifications and appearances may change without notice. All statements, technical information and recommendations herein are based on tests that we believed to be reliable, but the accuracy and completeness are not guaranteed. Before using, user should determine the suitability of the product for its intended use, and the user assumes all risks and liabilities whatsoever in connection therewith. Neither the seller nor the manufacturer shall be liable for any loss or damage, direct, incidental or consequential, including loss of profits or revenues arising from the use or inability to use the product. Any statements or recommendations shall have no effect unless contained in an agreement signed by authorized personnel of the seller and manufacturer.



# OP-8100 Spec 06

## THERMALLY CONDUCTIVE GAP FILLER



**SEM (North America) Inc.** +1 585-643-2000

Tel:

Fax:

Address

+1 585-427-7216 1555 Jefferson Road, **SEM Belgium bv** +32 59 560 270

Schatting 73, 8210 Zedelgem, Belgium SEM Asia Ltd.

+852 2686 8168 +852 2686 8268 Unit 1, 3/F Block A, New Trade Plaza, 6 On Ping Street, Shatin, N.T., Hong Kong SEM (Dongguan) Ltd.

+86-769-8334 1628 +86-769-8334 2028 No. 8A Qiaoxin Road, Qiaotou, Dongguan,Guangdong, China Postal code 523525

Specifications and appearances may change without notice. All statements, technical information and recommendations herein are based on tests that we believed to be reliable, but the accuracy and completeness are not guaranteed. Before using, user should determine the suitability of the product for its intended use, and the user assumes all risks and liabilities whatsoever in connection therewith. Neither the seller nor the manufacturer shall be liable for any loss or damage, direct, incidental or consequential, including loss of profits or revenues arising from the use or inability to use the product. Any statements or recommendations shall have no effect unless contained in an agreement signed by authorized personnel of the seller and manufacturer.